

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
8 January 2004 (08.01.2004)

PCT

(10) International Publication Number
WO 2004/002935 A1

(51) International Patent Classification⁷: **C07C 69/90**,
69/92, 69/618, C07D 493/04, C09K 19/58 // (C07D
493/04, 307:00, 307:00)

[NL/NL]; c/o Prof. Holstlaan 6, NL-5656 AA Eindhoven
(NL) WEGH, Rene, T. [NL/NL]; c/o Prof. Holstlaan 6,
NL-5656 AA Eindhoven (NL).

(21) International Application Number:
PCT/TB2003/002927

(74) Agent: **TOL, Arie, J., W.**; Philips Intellectual Property
& Standards, Prof. Holstlaan 6, NL-5656 AA Eindhoven
(NL).

(22) International Filing Date: 13 June 2003 (13.06.2003)

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD,
SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US,
UZ, VC, VN, YU, ZA, ZM, ZW.

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
02077561.5 28 June 2002 (28.06.2002) EP

(71) Applicant (*for all designated States except US*): **KONIN-
KLJKE PHILIPS ELECTRONICS N.V.** [NL/NL];
Groenewoudseweg 1, NL-5621 BA Eindhoven (NL).


(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **LUB, Johan**

[Continued on next page]

(54) Title: CHIRAL DOPANT WITH PHENYLETHANEDIOL FUNCTIONALITY



(57) Abstract: The invention pertains to a phenylethanol derivative having at least one polymerizable group, characterized in that the phenylethanol derivative further comprises at least one photo-convertible group for adjusting the helical twisting power of the phenylethanol derivative. According to a preferred embodiment the phenylethanol derivative has the formula wherein A stands for a bond or a p-phenylene group; B and B' are independently (O)p-CoH2o-O-CO-CR'=CH2, o being 2-12, p being 0 or 1, and R' being H or CH3; P stands for a CH2 or a C=O group; Q and Q' are independently selected from H, C1-C3 alkyl, C1-C3 alkoxy, halogen, and CN; n is an integer from 1 to 3; and m is an integer from 0 to 2; and wherein A stands for a bond or a p-phenylene group; B is (O)p-CoH2o-O-CO-CR'=CH2, o being 2-12, p is 1, and R' being H or CH3; P stands for a CH2 or a C=O group; Q is selected from H, C1-C3 alkyl, C1-C3 alkoxy, halogen, and CN; and m is an integer from 0 to 2.

**Published:**

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

Chiral dopant with phenylethanediol functionality

The invention pertains to a phenylethanediol derivative preferably having at least one polymerizable group, to a method for the preparation thereof, to a cholesteric composition and an optical element comprising said phenylethanediol derivative, and to the use of the phenylethanediol derivative in optical elements.

5

Chiral derivatives having a polymerizable group are known in the art. For instance, in WO 98/00428 chiral dopants were disclosed comprising an isosorbide moiety and ester groups. In this reference it is explained that these chiral dopants are used to induce or enhance the helical twist of the molecules of a liquid crystalline medium, which can be used to make cholesteric color filters (CCF's).

10

Other derivatives having a polymerizable group are known from WO 99/64383, disclosing optically active butane-1,2,3,4-tetraol derivatives for use in cholesteric filters. These derivatives can be polymerized and can also be used as chiral dopant in cholesteric networks.

15

All these prior art derivatives usually have high helical twisting power (HTP) values, but the pitch of the helix of the liquid crystalline molecules can only be adjusted by varying the concentration of the dopant. It would be a substantial advantage when at the same concentration of the chiral dopant different pitches of the helix could be attained. In WO 00/34808 other chiral dopants have been disclosed, i.e. menthone derivatives having both polymerizable and photo-isomerizable groups, and various methods of providing a variation in the pitch are discussed. These chiral dopants can be used in CCF's for reflective and transmissive LCD's (liquid crystal displays). Such filters are made by applying a solution of a mixture of nematic compounds, for instance diacrylates, a photosensitive chiral compound, and a photo-initiator onto a substrate by using a coating technique such as spin coating. By irradiation through a mask color formation is performed, after which the color is fixed by photopolymerization and the color film is obtained as a stable crosslinked film. The pitch p of the molecular helix depends on the concentration of the chiral dopant and is inversely proportional to a factor that is called the helical twisting power (HTP). The pitch of the helix and the direction of the helix (right or left handed helix) determine the wavelength at which

20

25

light is reflected from the cholesteric liquid crystals and whether the reflected light is polarized right or left handed. Its relatively high HTP values allow the use of low concentrations of chiral dopant, which is important since these dopants are expensive and difficult to make. It is further explained that a short pitch is sometimes demanded, whereas
5 for other applications a long pitch is required. This can be realized by adapting the concentration of the chiral dopant. Moreover, the pitch can be varied as a function of position in the film by the introduction of a photo-isomerizable chiral compound, preferably a chiral acrylate. The degree of conversion is determined by the radiation intensity, and the pitch of the cholesterically ordered material is determined by the extent of conversion of the photo-
10 isomerizable compound. A specific chiral dopant that satisfies these conditions was disclosed to be a menthone derivative, which is a benzene derivative with an ether group separated by a spacer from an acrylic moiety and at the para position having an ester group comprising a photo-isomerizable cyclohexylidene moiety. Although the principle as outlined in WO 00/34808 appears to be a substantial improvement to the art, the photo-isomerizable
15 menthone derivative as used is far from ideal since it has only limited thermal stability. Since heating steps are necessary to make LCD's (liquid crystalline displays) color filters comprising these menthone derivatives lose their optical performance. Furthermore, it is desirable to improve the alignment capability of the prior art menthone derivatives. It is further desired to find optical derivatives, which can be made of cheap starting materials.
20 Preferably, each of the enantiomers is commercially available.

It is therefore an object of the present invention to provide a chiral dopant with relatively high HTP values, and improved thermal stability and alignment capability, which can be prepared from inexpensive commercially available materials. It has now been
25 surprisingly found that phenylethanediol derivatives can be provided with photo-convertible groups to give derivatives with extremely good thermal stability, sufficiently high HTP values, and excellent alignment capability. These derivatives can be prepared starting from ethyl mandelate, of which both enantiomers are easily available. The invention therefore relates to phenylethanediol derivatives preferably having at least one polymerizable group,
30 characterized in that the phenylethanediol derivative further comprises at least one photo-convertible group suitable for adjusting the helical twisting power of the phenylethanediol derivative.


Persons skilled in the art will appreciate that in general any two chiral dopants and therefore also chiral dopants comprising, in accordance with the invention, a phenylethane diol, having a different chemical structures will have a different helical-twisting power. Furthermore, obviously, the helical-twisting power of a compound which is not a chiral dopant is different from a chiral dopant, the former being characterized by the absence of helical twisting power. Accordingly, persons skilled in the art will appreciate that any photochemical reaction known in the art as such can in principle be used as a basis to provide suitable embodiments of photo-convertible groups. In particular, photo-convertible groups may be used which upon irradiation become cyclic or, just the opposite, ring-open, or different types of rearrangements. Alternatively, photo-cleavable groups may be used such as those disclosed in US 5,668,614. Preferably however, the photo-convertible group is a photo-isomerizable group. Suitable photo-isomerizable groups comprise an olefinic moiety that can undergo E-Z isomerization upon irradiation. Examples of such groups are derived from styrene- and stilbene-like compounds.

The phenylethanediol derivatives of the invention preferably further comprise a polymerizable group. Suitable polymerizable groups, in particular photo-polymerizable groups, include but are not limited to epoxides, vinyl ethers, oxetanes, cinnamates, and thiolenes. A preferred (photo)-polymerizable group is the (meth)acrylate group. The phenylethanediol molecule contains two hydroxy groups, at least one, but preferably both, thereof being esterified or etherified with a substituent. The substituents comprise the photo-convertible and preferably photo-polymerizable groups. The photo-convertible and photo-polymerizable groups may be contained in the same or in different substituents. It also may be that the different substituents comprise the same or different photo-convertible and/or photo-polymerizable groups, or that the photo-convertible and photo-polymerizable groups are contained in only one of the ester or ether substituents, whereas the other hydroxy group of the phenylethanediol is a free hydroxy group or is esterified or etherified with a substituent that does not comprise a photo-convertible and/or photo-polymerizable group.

The phenylethanediol group is a group which, when esterified or etherified, enables or at least does not preclude the phenylethanediol derivative so obtained to be or become a chiral dopant, that is a compound which when added to a non-optically active liquid crystal composition, such as a nematic liquid crystal composition, changes that composition into an optically active composition, such as a chiral nematic composition (cholesteric composition) or modifies the optical properties of an optically active liquid crystal composition when added to such optically active liquid crystal composition. To

enable the formation of an optically active liquid crystal composition, a chiral dopant molecule generally has a chiral center, typically a chiral carbon atom, and a shape which is similar to the molecules of the liquid crystal composition to which the chiral dopant is to be added. In particular, in order to obtain suitable phenylethanol derivative in accordance with the invention the phenylethanol derivative is esterified or etherified with mesogenic groups or parts of the mesogenic groups. Such mesogenic groups or parts of such mesogenic are well known in the art. More specific phenylethanol derivatives in accordance with the invention may include but are limited to those comprising $-(T4-L4)_{q1}-T2-L2-PED-L1-T1-(L3-T3)_{q2}-$ wherein PED is the esterified or etherified phenylethanol group, L1 and L2, the same or different at each occurrence, a single bond, carbonyl, CH_2 , $-CH_2CH_2-$, $-CH=CH-$, ethynylene, $-OCH_2-$, L3 and L4, the same or different at each occurrence, L1, L2, thionyl, oxygen, sulfur carboxyl, $-C=N-$, $-N=N-$, amide, T1, T2, T3, T4, the same or different at each occurrence, a substituted or unsubstituted phenylene, naphthalene, cyclohexylene, or other C1-C15 aromatic or saturated ring wherein 1 to 6 carbon atoms may be replaced with N, O or S, and q_1 and q_2 , the same or different, 0 to 6.

Preferred phenylethanol derivatives were found to have the formula



wherein

A stands for a bond or a p-phenylene group;

B and B' are independently $(O)_p-C_6H_{2o}-O-CO-CR'=CH_2$, o being 2-12, p being 0 or 1, and R' being H or CH_3 ;

P stands for a CH₂ or a C=O group;

Q and Q' are independently selected from H, C1-C3 alkyl, C1-C3 alkoxy, halogen, and CN;

n is an integer from 1 to 3; and


m is an integer from 0 to 2.

5

The term C1-C3 alkyl means an alkyl group with 1 to 3 carbon atoms, i.e. methyl, ethyl, propyl, and isopropyl. The term C1-C3 alkoxy means an alkoxy group with these alkyl groups. The term halogen means a halogen atom, such as fluorine, chlorine, bromine, and iodine.

10

In another preferred embodiment the phenylethanedioi has the formula



wherein

A stands for a bond or a p-phenylene group;

15 B is (O)_p-C₆H_{2o}-O-CO-CR'=CH₂, o being 2-12, p is 1, and R' being H or CH₃;

P stands for a CH₂ or a C=O group;

Q is selected from H, C1-C3 alkyl, C1-C3 alkoxy, halogen, and CN; and


m is an integer from 0 to 2.

20

Although from a synthetic point of view it is preferred that in these compounds both 1- and 2-hydroxy substituents are the same, it is also possible to use compounds wherein the two substituents are different, i.e. wherein A, B, P, Q, o, p, and/or m are differently selected for the two substituents. When both substituents are the same, the synthesis can be simplified by using a direct etherification or esterification of


25 phenylethanedioi, without first selectively protecting the one of the hydroxy groups.

Examples of phenylethanediol derivatives according to this invention are:




5

(phenylethanediol 1)



10

(phenylethanediol 14)




15

(phenylethanediol 22)

The phenylethanediol derivatives according to the invention may be used as a cholesteric composition mixed with other chiral compounds, for instance such as with a non-isomerizable phenylethanediol derivative (phenylethanediol D) of the formula:

20



(phenylethanol D)

5

The phenylethanol derivatives of the invention can be prepared from L-ethyl or D-ethyl mandelate in which the hydroxy group is protected with a temporarily protective group, such as an ether group. The ethyl ester group of the protected ethyl mandelate can then be reduced in a common manner known in the art, such as reduction with
10 lithium aluminum hydride, sodium borohydride, and the like. The present modified synthesis enables to make phenylethanol derivatives that selectively have different substituents at their 1- and 2-hydroxy groups. The present method therefore comprises a) synthesizing a 1-hydroxy ether-protected phenylethanol, b) followed by etherification or esterification of the 2-hydroxy group of the 1-hydroxy ether-protected phenylethanol with an alcohol (or
15 derivative thereof) or acid, respectively, optionally comprising polymerizable and/or photo-convertible groups, c) then cleaving the ether-protective group to obtain a phenylethanol derivative with a free 1-hydroxy group, and optionally d) esterification of the free 1-hydroxy group with an acid, which optionally comprises one or more polymerizable and/or photo-convertible groups.

20


This method has the advantage that no separation is necessary of the 1-hydroxy ether-protected phenylethanol from the 2-hydroxy ether-protected, 1,2-dihydroxy ether-protected, and unprotected phenylethanol derivatives. The ether-protecting group can be any common group that is known in the art for the protection of hydroxy groups through an ether
25 linkage. Preferred ether-protective groups are the THP (tetrahydropyranyl) ether and the ethoxyethyl ether groups that are formed when a hydroxy group is reacted with 3,4-dihydro-2H-pyran and ethylvinylether, respectively, and which can easily be cleaved under mild acidic conditions to release the hydroxy group.

The alignment of the CCF based on these phenylethanedil derivatives and therefore the reflection intensity is significantly improved. Most importantly, the thermal stability is much higher than that of the menthone derivative based CCF's. Upon irradiation photo-conversion, particularly photo-isomerization occurs leading to an HTP change that is sufficient to change the color from blue to red. The concentration of the chiral photo-convertible compounds is chosen in such a way by making mixtures with non-chiral compounds, to obtain a blue reflecting layer before irradiation. A red layer is then obtained after a certain period of irradiation. If both a photo-convertible and a non-photo-convertible chiral dopant are used, e.g. phenylethanedils 1 or 14 or 22 together with D, and the concentrations are chosen properly, a layer can be obtained that reflects blue before irradiation and red in the photostationary state. This means that only the formation of a green color depends on the total UV dose, thus making the manufacture of a mask for pixelated irradiation very simple. This makes the phenylethanedil derivatives suitable for use in optical elements, preferably in optical color filters.

The invention is further illustrated by the following non-restrictive examples.

Example 1

Synthesis of (E)-(R)-4-(2-phenyl-2-(4-(6-acryloyloxyhexyloxy)benzoyloxyethyloxy)methyl 4'-hexyloxy stilbene (1)



A: (R)-2-(2-{4-[2-(4-Hexyloxy-phenyl)-vinyl]-benzyloxy}-1-phenyl-ethoxy)-tetrahydro-pyran (4).

5 0.75 g (3.35 mmole) of (R)-2-Phenyl-2-(tetrahydro-pyran-2-yloxy)-ethanol (2) were added to a solution of 0.4g (6.08 mmole) of powdered KOH (85%) in 6 ml of dimethylsulfoxide. After 10 min stirring 1 g (3 mmole) of (E)-4-chloromethyl-4'-hexyloxystilbene (3) was added in small portions. The reaction was stirred overnight at room temperature under N₂ atmosphere.

10 60 ml of water were added and the product was precipitated. The powder was filtered and washed with 25 ml of water and dried in air. 1.4 g of white-yellow powder was obtained.

B: (E)-(R)-4-(2-phenyl-2-hydroxyethoxy)methyl 4'-hexyloxy stilbene (6).

15

1.4 g of (R)-2-(2-{4-[2-(4-Hexyloxy-phenyl)-vinyl]-benzyloxy}-1-phenyl-ethoxy)-tetrahydro-pyran (4) were dissolved in 30 ml of ethanol. Hydrochloric acid was added dropwise to obtain an acidic medium. Then the mixture was refluxed for 30 min. Upon

cooling the product crystallized. The solid was filtered, washed with ethanol, and dried in a dessicator.


1 g of yellow powder was obtained (overall yield:74.5%)

- 5 C: (E)-(R)-4-(2-phenyl-2-(4-(6-acryloyloxyhexyloxy)benzoyloxyethyloxy)methyl 4'-hexyloxy stilbene (1).

0.26 g of N,N'-dicyclohexyl carbodiimide (2.25 mmole) were added to a mixture of 0.035 g (0.225 mmole) of 4-N,N-dimethylaminopyridine, 1 g (2.25 mmole) of
 10 (E)-(R)-4-(2-phenyl-2-hydroxyethyloxy)methyl 4'-hexyloxy stilbene (6), 0.66 g (2.25 mmole) of 4-(6-acryloyloxyhexyloxy)benzoic acid (5) and 10 ml of dichloromethane, and stirred in an ice-water bath. After 30 min the ice-water bath was removed and the reaction was stirred overnight at room temperature. The mixture was filtered through a silica pad and evaporated. The remaining solid was crystallized twice from alcohol to obtain 0.7 g of the product (47%)
 15 as a yellowish powder with mp 87°C.

Example 2

Synthesis of (E)-4-chloromethyl-4'-hexyloxystilbene (3).



A: (E)-4-hydroxymethyl-4'-hexyloxystilbene (7).

115 mg (16.5 mmole) of Li were dissolved in 75 ml of ethanol under nitrogen
 25 atmosphere. Then 2.05 g (15 mmole) of aldehyde 4-hydroxymethylbenzaldehyde were added and the mixture was cooled in an ice bath. Then 5.148 g (15 mmole) of (4-hexyloxy-benzyl)-triphenyl-phosphonium bromide were added. The mixture was stirred in the ice bath under

nitrogen for 30 min, and then stirred at room temperature for 3 h. 2.5 ml of water were added and the precipitate was collected on a filter and washed with 10 ml of ethanol. After drying over silica in a dessicator 1.75g of white powder was obtained. Yield: 37 %.


5 *B: (E)-4-chloromethyl-4'-hexyloxystilbene (3).*

To a solution of 1.7 g (5.5 mmole) of (E)-4-hydroxymethyl-4'-hexyloxystilbene (7) in 12 ml of dichloromethane cooled in an ice bath under N₂ atmosphere were added dropwise 0.5 ml of thionylchloride in 3 ml of dichloromerthane.

10 After 1.5 h 16 ml of water were added and the organic layer was separated. It was washed with 12 ml of brine, dried over MgSO₄ and the solvent was evaporated. A white solid was obtained which was recrystallized from 80 ml of a 1:1 mixture of hexane and ethanol. 1.1g of white crystals were obtained (yield: 60%).

15 **Example 3**

Synthesis of (R)-2-Phenyl-2-(tetrahydro-pyran-2-yloxy)-ethanol (2).



20 **A: (R)-(-)-ethyl-2-phenyl-(tetrahydropyranyloxy)-acetate. (8)**

A solution of 10 g (55 mmole) of ethyl(R)-(-)-mandelate, 0.7 g (2.8 mmole) of pyridinium 4-toluenesulfonate and 7.6 ml (83.3 mmole) of 3,4-dihidro-2H-pyran in 50 ml of dichloromethane was stirred at room temperature for 24 h. The solution was extracted once
25 with 25 ml of water and once with 25 ml of NaHCO₃ (5%). It was dried over magnesium sulfate and the solvent was evaporated to leave 14.28 g (97%) of a clear oil.


B: (R)-2-Phenyl-2-(tetrahydro-pyran-2-yloxy)-ethanol (2).

30 A solution of 4 g (15.1 mmole) of (R)-(-)-ethyl-2-phenyl-2-(tetrahydropyranyloxy)acetate (8) in 75 ml of dry ether was added dropwise to a stirred suspension of 1.72 g (45.3 mmole) of lithium aluminium hydride and 50 ml of ether at room

temperature. After the addition was completed, the mixture was refluxed for additional 2 h, then cooled in an ice bath, and treated carefully subsequently with 1.72 ml of water, 1.72 ml of 15% sodium hydroxide, and 5.4 ml of water. After being stirred for additional 30 min, the mixture was filtered with suction, and the precipitate (aluminum salts) was washed with ether. The combined ethereal solution was dried over magnesium sulfate, and the solvent was evaporated to leave 3.3 g of a clear oil (97%).

Example 4

Synthesis of (R)-4-(4-(6-Acryloyloxyhexyloxy)-cinnamic acid 2-[4-(4-(6-acryloyloxyhexyloxybenzoyloxy)benzoyloxy)]-1-phenyl-ethyl ester (9).



A: (R)- 4-(4-(6-acryloyloxyhexyloxybenzoyloxy)benzoic acid 2-(tetrahydropyran-2-yloxy)-2-phenyl-ethyl ester.(11).

A mixture of 2.22 g (0.01 mol) of (R)-2-Phenyl-2-(tetrahydro-pyran-2-yloxy)-ethanol (2)., 4.12g (0.01 mole) of 4-(4-(6-acryloyloxyhexyloxy)benzoyloxy)benzoic acid

(13), 0.12 g (1 mmole) of 4-N,N-dimethylaminopyridine and 50 ml of dichloromethane was stirred under nitrogen atmosphere in an ice-water bath. Then 2.06 g of N,N'-dicyclohexyl carbodiimide were added. After 2.5 h the bath was removed. After 3 days the mixture was filtered over a silica pad and the solvent was evaporated to leave a clear oil that became a white solid upon standing.

B: (R)- 4-(4-(6-acryloyloxyhexyloxybenzoyloxy)benzoic acid 2-hydroxy-2-phenyl-ethyl ester.(12).


The crude (R)- 4-(4-(6-acryloyloxyhexyloxybenzoyloxy)benzoic acid 2-(tetrahydropyran-2-yloxy)-2-phenyl-ethyl ester.(11) was dissolved in 35 ml of ethanol and 0.25g (1 mmole) of pyridinium 4-toluensulfonate and 40 mg of 4-methoxyphenol were added. The mixture was heated at 55°C for 15 h. After cooling to 0°C the product precipitated. 3.2 g of a white solid was obtained (60%).

C: (R)-4-(6-Acryloyloxy-hexyloxy)-cinnamic acid 2-[4-(4-(6-acryloyloxyhexyloxybenzoyloxy)benzoyloxy)]-1-phenyl-ethyl ester (9).

A mixture of 3.2 g (6 mmole) of (R)- 4-(4-(6-acryloyloxyhexyloxybenzoyloxy)benzoic acid 2-hydroxy-2-phenyl-ethyl ester(12), 1.91 g (6 mmole) of 4-(6-acryloyloxyhexyloxy)cinnamic acid (13), 0.073 g (0.6 mmole) of 4-N,N-dimethylaminopyridine and 40 ml of dichloromethane was stirred atmosphere in an ice-water bath. Then 1.3 g of N,N'-dicyclohexyl carbodiimide were added. After 2.5 h the bath was removed. The mixture was stirred overnight under and then filtered through a silica pad. The solvent was evaporated to leave clear oil that became a white waxy solid upon standing. The solid was washed twice with ethanol. 5.3 g of a white powder was obtained (68%) with mp 81°C.

Example 5


Synthesis of (R)-4-(6-Acryloyloxy-hexyloxy)-cinnamic acid 2-[4-(4-(6-acryloyloxyhexyloxybenzoyloxy)benzoyloxy)]-2-phenyl-ethyl ester (14).



This compound was prepared in the same way as (R)-4-(6-Acryloyloxy-hexyloxy)-cinnamic acid 2-[4-(4-(6-acryloyloxyhexyloxybenzoyloxy)benzoyloxy)-1-phenyl-ethyl ester (9). In this reaction sequence compound 10 was changed for 13. Mp 53°C.

Example 6

Synthesis of 4-(4-(6-acryloyloxyhexyloxy)benzoyloxy)benzoic acid (10)



A: 4-Hydroxy-benzoic acid ethoxymethyl ester (15).

36.7 ml (0.26 mole) of triethylamine were added under N₂ atmosphere to a solution of 36.1 g (0.26 mole) of 4-hydroxybenzoic acid in 200 ml of dichloromethane. The mixture was cooled in an ice-water bath, and 24.5 ml (0.26 mole) of chloromethyl ethyl ether in 100 ml of dichloromethane were added dropwise.

After stirring for 1.5 h, the mixture was washed once with 150 ml of water then with 13 ml of hydrochloric acid (2.4 M) in 150 ml of water. Finally the solution was

washed with 150 ml of saturated solution of NaHCO_3 and filtered through a filter paper. The solvent was evaporated. The oil was dissolved in 500 ml of diethyl ether and washed once with 250 ml of water, once with 250 ml of saturated solution of NaHCO_3 , and finally with 250 ml of brine. The organic layer was dried over MgSO_4 , and the solvent was evaporated.

5 42.2 g of a clear oil (77%) were obtained, after few minutes it crystallized as white crystals.

B: ethoxymethyl 4-(4-(6-acryloyloxyhexyloxy)benzoyloxy)benzoate (16).

To a solution of 42.2 g (0.20 mole) of 4-Hydroxy-benzoic acid ethoxymethyl ester (15) in 520 ml of dichloromethane were added 58.3 g (0.2 mole) of 4-(6-acryloyloxy-hexyloxy)-benzoic acid (5) and 2.4 g (0.02 mole) of 4-N,N-dimethylaminopyridine under N_2 atmosphere. The mixture was cooled in an ice-water bath. After few minutes 41.15 g (0.2 mole) of N,N-dicyclohexyl carbodiimide were added. Then the ice-water bath was removed. It was stirred at room temperature under N_2 for one night. Then the mixture was filtered and
15 extracted twice with 300 ml of hydrochloric acid (2.4 M).

The organic layer was passed through a filter paper and the solvent was evaporated to leave 98.5 g of a clear oil (100%).

C: 4-(4-(6-acryloyloxyhexyloxy)benzoyloxy)benzoic acid (10).


20

98.5 g (0.2 mole) of ethoxymethyl 4-(4-(6-acryloyloxyhexyloxy)benzoyloxy)benzoate (16) were dissolved in 400 ml of ethanol and 5 g (0.02 mole) of pyridinium 4-toluensulfonate and 20 mg of 4-methoxyphenol were added. The mixture was heated at 60°C for 15 h. After cooling down at room temperature the product
25 crystallized. It was collected, washed with 300 ml of ethanol, and dried in a desiccator 55.3 g of a white powder (67 %) were obtained.

Example 7

Synthesis of 4-(6-acryloyloxyhexyloxy)cinnamic acid (13).

30



A: 4-(6-hydroxyhexyloxy)cinnamic acid (17).

5 To a mixture of 24.62 g (0.15 mole) 4-hydroxycinnamic acid and 0.29 g (1.65 mmole) of potassium iodide in 60 ml of ethanol was added under nitrogen atmosphere in 10 min a solution of 20.72 g (0.314 mole) of potassium hydroxide in 60 ml of water using a dropping funnel. The resulting solution was heated to 30-40°C and 6-chlorohexanol (22.54 g, 0.165 mole) was then added in about 10 min. The solution was then refluxed overnight. After
10 cooling 70 ml of water were added to the solid reaction mixture, and the ethanol was removed using a rotary evaporator. The residue was cooled in an ice/water bath and 70 ml of conc. hydrochloric acid were added while stirring. The solid was collected and washed with water. Then the solid was stirred at 50°C with 250 ml of acetone. After drying at 100°C in vacuo 24.5 g (62%) of the product was obtained.

15


B: 4-(6-acryloyloxyhexyloxy)cinnamic acid (13).

A mixture of 21.15 g (0.08 mole) 4-(6-hydroxyhexyloxy)cinnamic acid (13), 11.63 g (0.096 mole) N,N-dimethylaniline 8.69 g (0.096 mole) acryloyl chloride, 0.05 g of
20 2,6-di-*t*-butyl-4-methylphenol and 60 ml of 1,4-dioxane was heated at 60°C under nitrogen atmosphere. After 2 h heating at 60°C the mixture was filtered and dropped into a mixture of 1000 ml of water, 400 g of ice and 10 ml of 2.4 N hydrochloric acid while stirring. The solid precipitate was filtered off and recrystallized from 350 ml of ethanol. The solid was dried in a desiccator over silica gel. Yield: 19.7 g (77.3%).

25

Example 8

Synthesis of (R)-4-(4-(6-Acryloyloxyhexyloxy)benzoyloxy)cinnamic acid 2-(4-(6-acryloyloxyhexyloxy)benzoyloxy)-2-phenyl-ethyl ester (18).



5

A: (R)-4-(4-(6-Acryloyloxyhexyloxy)benzoyloxy)cinnamic acid 2-(tetrahydropyran-2-yloxy)-2-phenyl-ethyl ester (20).

To a solution of 2.2 g (10 mmole) of (R)-2-Phenyl-2-(tetrahydro-pyran-2-yloxy)-ethanol (2) in 40 ml of dichloromethane were added 4.4 g (10 mmole) of 4-(4-(6-acryloyloxyhexyloxy)benzoyloxy)cinnamic acid (19) and 0.12 g (1 mmole) of 4-N,N-dimethylaminopyridine. The mixture was cooled in an ice-water bath. After few minutes were added 2 g (10 mmole) of N,N-dicyclohexyl carbodiimide. Then the ice-water bath was removed. The mixture was stirred at room temperature for two days. Then it was filtered through a silica pad and the solvent was evaporated at 40°C. 6.36 g of a white solid (99%) were obtained.

B: (R)-4-(4-(6-Acryloyloxyhexyloxy)benzoyloxy)cinnamic acid 2-hydroxy-2-phenyl-ethyl ester (21).

20


6.4 g of (R)-4-(4-(6-Acryloyloxyhexyloxy)benzoyloxy)cinnamic acid 2-(tetrahydropyran-2-yloxy)-2-phenyl-ethyl ester (**20**) (9.8 mmole) were dissolved in 35 ml of absolute ethanol and 0.5 g (2 mmole) of pyridinium 4-toluensulfonate and 40 mg of 4-methoxyphenol (to avoid polymerization) were added. The mixture was heated at 55°C for 20 h. After cooling to room temperature, a white powder precipitated. It was filtered and washed with ethanol. It was dried in a dessicator with silica. 3 g of a white solid (55%) were obtained.

C: (R)-4-(4-(6-Acryloyloxyhexyloxy)benzoyloxy)cinnamic acid 2-(4-(6-acryloyloxyhexyloxy)benzoyloxy)-2-phenyl-ethyl ester (**18**).

0.56 g (2.7 mmole) of N,N-dicyclohexyl carbodiimide were added to a solution of 1.5 g (2.7 mmole) of (R)-4-(4-(6-acryloyloxyhexyloxy)benzoyloxy)cinnamic acid 2-hydroxy-2-phenyl-ethyl ester (**21**), 0.8 g (2.7 mmole) of 4-(6-acryloyloxy-hexyloxy)-benzoic acid (**5**) and 0.03 g (0.27 mmole) of 4-N,N-dimethylaminopyridine in 20 ml of dichloromethane, and cooled in an ice-water bath. After 3 h the ice-water bath was removed. The mixture was stirred at room temperature for two days. Then the mixture was filtered through a silica pad and the solvent was evaporated. After crystallization from ethanol, 1.2 g of the product (53%) were obtained with mp 97°C.

Example 9

Synthesis of (R)-4-(4-(6-Acryloyloxyhexyloxy)benzoyloxy)cinnamic acid 2-(4-(6-acryloyloxyhexyloxy)benzoyloxy)-1-phenyl-ethyl ester (**22**).




This compound was prepared in the same way as (R)-4-(4-(6-acryloyloxyhexyloxy)benzoyloxy)cinnamic acid 2-(4-(6-acryloyloxyhexyloxy)benzoyloxy)-

2-phenyl-ethyl ester (18). In this reaction sequence compound 19 was changed for 5. mp 80°C.

Example 10

5 Synthesis of 4-(4-(6-acryloyloxyhexyloxy)benzoyloxy)cinnamic acid (19)



10 A: 4-Hydroxy- cinnamic acid ethoxymethyl ester (23).

To a solution of 16 g (100 mmole) of 4-hydroxycinnamic acid in 80 ml of dichloromethane were added 14 ml (100 mmole) of triethylamine under an N₂ atmosphere. The mixture was cooled in an ice-water bath, and then, 9.3 ml (100 mmole) of chloromethyl ethyl ether in 40 ml of dichloromethane were added dropwise. After stirring overnight, the solution was extracted once with 60 ml of water and once with a solution of 60 ml 0.1 M hydrochloric acid. Finally, the solution was extracted with 60 ml of saturated solution of NaHCO₃ and dried over MgSO₄. The solvent was evaporated and 18.7 g of a clear oil were obtained (purity: 90% and yield: 84%).

20

B: Ethoxymethyl 4-(4-(6-acryloyloxyhexyloxy)benzoyloxy)cinnamate (24)

15.7 g (0.076 mole) of N,N-dicyclohexyl carbodiimide were added to a solution of 18.7 g (0.076 mole) of 4-hydroxycinnamic acid ethoxymethyl ester (23) (90% pure), 22.2 g (0.076 mole) of 4-(6-acryloyloxy-hexyloxy)-benzoic acid (5) and 0.93 g (0.0076 mole) of 4-N,N-dimethylaminopyridine in 200 ml of dichloromethane, cooled in an ice-water bath. After two hours the ice-water bath was removed. The mixture was stirred at room temperature overnight. Then it was filtered through a silica pad and the solvent was evaporated. 15 g of the product (40%) were obtained after crystallization from ethanol.


10 C: 4-(4-(6-Acryloyloxyhexyloxy)benzoyloxy)cinnamic acid (19).

14.9 g of ethoxymethyl 4-(4-(6-acryloyloxyhexyloxy)benzoyloxy)cinnamate (24) (30 mmole) were dissolved in 60 ml of absolute ethanol and 0.75 g (3 mmole) of pyridinium 4-toluenesulfonate and minor amounts of 4-methoxyphenol (to avoid the polymerization) were added. The mixture was heated at 60°C (bath temperature) for 13 h. After cooling to room temperature, a white solid appeared. It was filtered, washed with ethanol and dried in a dessicator with silica overnight. 12.7g of a white solid were obtained (yield: 97 %).

20

Example 11

Synthesis of (R)-4-(6-Acryloyloxyhexyloxy)cinnamic acid 2-(4-(6-acryloyloxyhexyloxy) cinnamoyloxy)-1-phenyl-ethyl ester (25)



25

3 g (14.5 mmole) of N,N'-dicyclohexyl carbodiimide were added to a mixture of 1 g (7.25 mmole) of R-(-)-1-phenyl-1,2-ethanediol, 4.6 g (14.5 mmole) of 4-(6-acryloyloxyhexyloxy)cinnamic acid (13), 0.18 g (1.45 mmole) of 4-N,N-

5 dimethylaminopyridine and 40 ml of dichloromethane, cooled in an ice-water bath. The mixture was stirred at room temperature for two days. After filtration, the solvent was evaporated. 3.84 g of the product (72%) were obtained as a viscous oil after elution with dichloromethane/ethyl acetate : 98/2 over silica.

10 Example 12

On a clean glass surface polyimide was applied by spin-coating, followed by baking and rubbing. A homogeneous mixture of

0.156 g of compound 25

0.667 g of acrylate I


15 0.167 g of acrylate II

0.01 g of Darocur® 4265 (ex Ciba Geigy)


in 1.00 g of xylene containing 100 ppm of 4-methoxyphenol as inhibitor, was filtered and spin-coated with a Convac spin-coater for 30 sec at 1500 rpm on the polyimide surface. After color formation by UV irradiation at 365 nm through a photo mask in air, the

20 film was photopolymerized under nitrogen by irradiation at 405 nm for 10 min. The CCF was obtained after 90 min postcuring at 150°C.

The chemical structures of the acrylates I and II are:



acrylate I



acrylate II

Example 13

In a manner analogous to that of Example 12 a color filter was made with a mixture of

5 0.053 g of compound 25

0.067 g of isosorbide derivative I

0.696 g of acrylate I


0.174 g of acrylate II

0.01 g of Darocur® 4265 (ex Ciba Geigy)

10 in 1.00 g of xylene containing 100 ppm of 4-methoxyphenol as inhibitor. The helical twisting power of the isosorbide derivative I is opposite relative to compound 25. The concentrations of the chiral dopants were chosen such that the color filter reflects at 650 nm (red) before isomerisation and at 450 nm (blue) after isomerisation.

The chemical structure of isosorbide derivative I is:

15



Isosorbide derivative I

20 Example 14

In a manner analogous to that of Example 12 a color filter was made with a mixture of

0.19 g of compound 18

0.64 g of acrylate I

25 0.16 g of acrylate II

0.01 g of Darocur® 4265 (ex Ciba Geigy)

in 1.00 g of xylene containing 100 ppm of 4-methoxyphenol as inhibitor.

30 Example 15 (comparative)

Example 12 was repeated with a mixture of
0.14 g of menthone derivative of WO 98/00428 (compound of Fig. 2B)
0.68 g of acrylate I
0.17 g of acrylate II
5 0.01 g of Darocur® 4265 (ex Ciba Geigy)
instead of the mixture of Example 13.

The spectra of Fig. 1A and B show the improvements obtained with the new phenylethandiol dopant. Fig. 1A shows the transmission spectra of the CCF of Example 12
10 (according to the invention) before heating and after heating at 200°C in air for the indicated times. Fig. 1B shows the transmission spectra of the CCF of Example 15 (comparative example) before heating and after heating at 200°C in air for the indicated times. In both cases the reflection band, i.e. the minimum of transmission, is positioned around 450 nm, i.e. in other words both layers reflect blue light. In Fig. 1A the intensity of the reflection band is
15 large (minimum transmission 5%), and the transmission in wavelength regions other than the reflection band is high (80-90%). This demonstrates the good alignment of the molecules, resulting in a nearly perfect helical structure. In Fig. 1B the intensity of the reflection band is small (minimum transmission 30%), and the transmission in wavelength regions other than the reflection band is low (~80% at long wavelength declining to ~30% at short wavelength).
20 This demonstrates the bad alignment of the molecules, which results in an imperfect helical structure.

Upon heating at 200°C, the reflection band in Fig. 1B shifts significantly to the left (~4% after 5 hours), whereas the reflection band in Fig. 1A does not shift at all. Moreover, the intensity of the reflection band in Fig. 1B decreases upon heating, whereas the
25 intensity of the reflection band in Fig. 1A does not. Hence, the thermal stability of the CCF with the phenylethandiol derivative as dopant is clearly better than that of the CCF with the menthone derivative as dopant.

The above results are obtained for a blue reflecting layer. For CCF's reflecting other colors the results are similar.

30 The spectra of example 14 show results similar to those of example 12 (Fig. 1A).

CLAIMS:

1. A phenylethanol derivative, characterized in that the phenylethanol derivative comprises at least one photo-convertible group suitable for adjusting the helical twisting power of the phenylethanol derivative.

5 2. The phenylethanol derivative of claim 1 further having at least one polymerizable group.

3. The phenylethanol derivative of claim 1 or 2 wherein the photo-convertible group is a photo-isomerizable group.


10

4. The phenylethanol derivative of claim 3 wherein the photo-isomerizable group is an olefinic group.

15 5. The phenylethanol derivative of any one of claims 1-4 wherein the polymerizable group is a (meth)acrylate group.

6. The phenylethanol derivatives of any one of the preceding claims wherein the phenylethanol has the formula

25



wherein

A stands for a bond or a p-phenylene group;


5 B and B' are independently $(O)_p-C_0H_{2o}-O-CO-CR'=CH_2$, o being 2-12, p being 0 or 1, and R' being H or CH_3 ;

P stands for a CH_2 or a $C=O$ group;

Q and Q' are independently selected from H, C1-C3 alkyl, C1-C3 alkoxy, halogen, and CN;
n is an integer from 1 to 3; and

10 m is an integer from 0 to 2.

7. The phenylethanol derivative of any one of the preceding claims wherein the phenylethanol has the formula



wherein

A stands for a bond or a p-phenylene group;

B is $(O)_p-C_6H_{2o}-O-CO-CR'=CH_2$, o being 2-12, p is 1, and R' being H or CH_3 ;

5 P stands for a CH_2 or a $C=O$ group;

Q is selected from H, C1-C3 alkyl, C1-C3 alkoxy, halogen, and CN; and

m is an integer from 0 to 2.


8. A method for the preparation of the phenylethanol derivative of claim 1 by
 10 the steps of a) synthesizing a 2-hydroxy ether-protected phenylethanol, b) followed by
 etherification or esterification of the 1-hydroxy group of the 2-hydroxy ether-protected
 phenylethanol with an alcohol (or derivative thereof) or acid, respectively, optionally
 comprising polymerizable and/or photo-convertible groups, c) then cleaving the ether-
 protective group to obtain a phenylethanol derivative with a free 2-hydroxy group, and
 15 optionally d) esterification of the free 2-hydroxy group with an acid which optionally
 comprises one or more polymerizable and/or photo-convertible groups.

9. A cholesteric composition comprising the phenylethanol derivative of any
 one of claims 1-7.

20

10. An optical element, preferably an optical color filter, comprising the
 phenylethanol derivative of any one of claims 1-7.

11. Use of the phenylethanol derivative of any one of claims 1-7 in optical
 25 elements.



wherein

A stands for a bond or a p-phenylene group;

B is $(O)_p-C_6H_{2o}-O-CO-CR'=CH_2$, o being 2-12, p is 1, and R' being H or CH_3 ;

5 P stands for a CH_2 or a $C=O$ group;

Q is selected from H, C1-C3 alkyl, C1-C3 alkoxy, halogen, and CN; and

m is an integer from 0 to 2.

1/1




FIG.1A




FIG.1B

INTERNATIONAL SEARCH REPORT

International Application No

PCT/IB 03/02927

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C07C69/90 C07C69/92 C07C69/618 C07D493/04 C07D493/04
 //(C07D493/04, 307:00, 307:00)

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C07C C07D C09K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	J. A. REGO ET AL: "Synthesis of Chiral Networks for Polymer Stabilized Cholesteric Texture (PSCT) Displays" POLYMER PREPRINTS, vol. 38, no. 1, April 1997 (1997-04), pages 364-365, XP008024494	1-5, 9-11
A	page 364, compounds 2 and 3	6-8
A	the whole document --- EP 0 643 318 A (SEIKO EPSON CORP) 15 March 1995 (1995-03-15) page 22, line 40 -page 23, line 50; claim 28 --- -/--	1, 9-11

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- * & * document member of the same patent family

Date of the actual completion of the international search

17 November 2003

Date of mailing of the international search report

27/11/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+31-70) 340-3016

Authorized officer

Hass, C

INTERNATIONAL SEARCH REPORT

International Application No

PCT/IB 03/02927

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 98 00428 A (MERCK PATENT GMBH; NOLAN PATRICK (GB); PARRI OWAIN (GB); FARRAND L) 8 January 1998 (1998-01-08) cited in the application claims ---	1,9-11
A	WO 99 64383 A (ROLIC AG; BUCHEKER RICHARD (CH); CHERKAOUI ZOUBAIR MOHAMMED (CH);) 16 December 1999 (1999-12-16) cited in the application claims 1,13-17; example 4 ---	1,9-11
A	WO 00 34808 A (LUB JOHAN; KONINKL PHILIPS ELECTRONICS NV (NL); WITTE PETER VAN DE) 15 June 2000 (2000-06-15) cited in the application claims 1,15; figures 2A,2B,2C,2E ---	1,9-11
A	US 5 668 614 A (CHIEN LIANG-CHY ET AL) 16 September 1997 (1997-09-16) cited in the application the whole document -----	1,9-11

INTERNATIONAL SEARCH REPORT

International Application No

PCT/IB 03/02927

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0643318	A	15-03-1995	DE 69431941 D1	06-02-2003
			DE 69431941 T2	30-04-2003
			EP 0643318 A1	15-03-1995
			WO 9423331 A1	13-10-1994
			KR 166943 B1	20-03-1999
			SG 87736 A1	16-04-2002
			TW 439989 Y	07-06-2001
			US 5686017 A	11-11-1997
			US 6261650 B1	17-07-2001
			US 5993689 A	30-11-1999
WO 9800428	A	08-01-1998	CN 1420382 A	28-05-2003
			CN 1223657 A ,B	21-07-1999
			DE 19781752 T0	02-09-1999
			WO 9800428 A1	08-01-1998
			GB 2329636 A ,B	31-03-1999
			JP 2000515496 T	21-11-2000
			KR 2000022497 A	25-04-2000
			US 6217792 B1	17-04-2001
WO 9964383	A	16-12-1999	AU 3950499 A	30-12-1999
			CN 1305447 T	25-07-2001
			EP 1086068 A1	28-03-2001
			WO 9964383 A1	16-12-1999
			JP 2002517475 T	18-06-2002
			US 6607677 B1	19-08-2003
WO 0034808	A	15-06-2000	CN 1295673 T	16-05-2001
			WO 0034808 A1	15-06-2000
			EP 1053493 A1	22-11-2000
			JP 2002532732 T	02-10-2002
			TW 424161 B	01-03-2001
			US 2002191945 A1	19-12-2002
			US 6459847 B1	01-10-2002
US 5668614	A	16-09-1997	NONE	